

TULSION[®] MB-108 P

Mixed Bed Ion Exchange for Production of Ultra Pure Water

TULSION[®] MB-108 P is a mixture of strongly acidic cation exchange resin **TULSION[®] T-42** in Hydrogen form and strongly basic anion exchange resin **TULSION[®] A-23 P** in Hydroxide form in 1:1 volumetric ratio.

TULSION[®] MB-108 P is designed for use in the production of water of the highest quality. **TULSION[®] MB-108P** is the ideal choice for electronic industries which manufacture semi conductors and television tubes, etc.

TYPICAL CHARACTERISTICS – MB-108P

RESIN NAME	TULSION T-46 H	TULSION A-33 OH
Type	: Strong Acid Cation Exchange Resin	Strong Base Anion Exchange Resin
Matrix structure	: Cross linked polystyrene	Cross linked polystyrene
Functional group	: Sulphonic acid	Quaternary Ammonium Type I
Physical form	: Moist spherical bead	Moist spherical bead
Ionic form	: Hydrogen	Hydroxide
Screen size USS (wet)	: 16 - 50	16 - 50
Particle size (mm)	: 0.3 - 1.2	0.3 - 1.2
Fines content	: Less than 1% passing through 50 US mesh	
Total exchange capacity	: 1.8 meq/ml min of 99% in H form	1meq/ml min. 90% in OH form & max.1% in Cl form.
Moisture content %	: 52 ± 3	60 ± 3
Backwash settled density gms/ 1	: Approximately 750	
Temperature stability (max.)	: 250° F / 120° C	175° F / 80° C
pH range	: 0 -14	0 -14
Bead strength	: Average not less than 500 g/bead by Chatillion test	Average not less than 250 g/bead by Chatillion test
Solubility	: Insoluble in all common solvents	Insoluble in all common solvents
Impurities	: Fe<50 ppm.	
Volume Ratio	1	2

TESTING

The sampling and testing of ion exchange resins is done as per standard testing procedures, namely ASTM D-2187 and IS-7330, 1998.

PACKING

Super sacks	1000 liters
MS drums	180 liters
HDPE lined bags	25 liters

Super sacks	35 cft
Fiber drums	7 cft
HDPE lined bags	1 cft

For Handling, Safety and Storage requirements please refer to the individual Material Safety Data Sheets available at our offices. The data included herein are based on test information obtained by Thermax Limited. These data are believed to be reliable, but do not imply any warranty or performance guarantee. Tolerances for characteristics are as per BIS/ASTM. We recommend that the user should determine the performance of the product by testing on own processing equipment.

For further information, please contact:



THERMAX

THERMAX LIMITED
CHEMICAL DIVISION

An ISO 9001 Company
97-E, GENERAL BLOCK,
M.I.D.C. BHOSARI,
PUNE- 411 026, INDIA
TEL.: +91(20) 2712 0181, 2712 0169
FAX: +91(20) 2712 0206
E-mail: resins@thermaxindia.com
Website: www.thermaxindia.com/chemical

USA Office :
THERMAX INC.

40440 Grand River Avenue,
Novi, Michigan 48375
U.S.A.
Tel: 248-474-3050
Fax: 248-474-5790

In view of our constant endeavour to improve the quality of our products, we reserve the right to change their specifications without prior notice.

Menu

Back